Jigsaw
RUBBER MATTING

PRODUCT TEST DOCUMENTATION

Test Certificate Class 0 edited

Supplied by Jigsaw Rubber Matting, a trading name of Jigsaw Industrial Ltd.

The original manufacturer or independent laboratory report follows in full. Its issuer, applicant, test results and original references have been retained. Jigsaw Rubber Matting is the retailer, not the testing body.

For product advice and sales enquiries, contact our team.

01260 272313 | info@rubber-matting.co.uk
www.rubber-matting.co.uk

FORM NO : NTH/CHN/F5

451173

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

परीक्षण प्रमाण पत्र
TEST CERTIFICATE

INTERIM/FINAL REPORT

Number of Copies issued Single				
परीक्षण प्रमाण पत्र सं Test Certificate No	जारी होने की तिथि Date of Issue	कोड नं Code No	पृष्ठ Page	पृष्ठों की संख्या No of Pages
NTH(SR)/EL(C)/2020/0049B-M	29/10/2020	Manual	1	2

जिसे जारी करना है Issued To	:	COBA Europe Ltd,
पता Address	:	Marlborough Drive, Fleckney, Leicester, LE8 8UR, United Kingdom
ग्राहक का सन्दर्भ सं एवं दिनांक Customer's Ref. No.	:	By Mail Date: 13/10/2020
पंजिका सं एवं दिनांक Register No & Date	:	0049B-M/NTH(SR)/EL(C)/21/10/2020
परीक्षण सामग्री का विवरण Description of Test Item	:	Electrical Insulating matting made of Elastomer, Class – 0
परीक्षण सामग्री का पहचान Identification of Test Item	:	Marking :As in the attached sheet "Annexure".
नमूना का विशिष्टि (यदि हों) Product Specification (If any)	:	IEC 61111 Edition 2.0 2009-04
नमूना प्राप्ति की तिथि Date of Receipt of the Test Item	:	21/10/2020
कार्य सम्पादन की तिथि Date(s) of Performance of Tests	:	From: 21/10/2020 To: 29/10/2020
व्यावहृत प्रणाली का पहचान Method(s) used for Test	:	Tests as per IEC 61111 Edition 2.0 2009-04
नमूना प्रकिया जहाँ प्रासंगिक हों Sampling Procedure where relevant	:	Not Applicable

Tested By	Checked By	Approved By
V.Sivaguru	Sriilayrajj Soundararajan	Sriilayrajj Soundararajan
SO Electrical	Scientist- C (Electrical)	Scientist- C (Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

परीक्षण प्रमाण पत्र
TEST CERTIFICATE

INTERIM/FINAL REPORT

Number of Copies issued	Single				
परीक्षण प्रमाण पत्र सं Test Certificate No	जारी होने की तिथि Date of Issue	कोड नं Code No	पृष्ठ Page	पृष्ठों की संख्या No of Pages
NTH(SR)/EL(C)/2020/0049B-M	29/10/2020	Manual	1	2

Sl. No.	Test Name	Test Result	Limit
1	Test	As in the attached sheet "Annexure" and the Annexure contains 05 page	As in the attached sheet "Annexure"

टिप्पणी
Note : i).The average ambient conditions of the laboratory during the above tests were as follows:Room temperature, deg C: 28+/-2, Relative humidity, percent: 70 to 75%.
ii).The Oil Resistance test was carried out by transformer oil as requested by the firm.

कैफियत
Remarks : Comments offered against each test.

Tested By	Checked By	Approved By
V.Sivaguru	Sriilayrajj Soundararajan	Sriilayrajj Soundararajan
SO Electrical	Scientist- C (Electrical)	Scientist- C (Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH(SR)/EL(C)/2020/0049B-M	29.10.2020	Manual	01	05

1. Description of the sample :

a. Nomenclature : **Electrical Insulating matting made of Elastomer, Class – 0**
b. Size : 1m x 5m
c. Quantity : 1 roll
d. Colour Code : Not Avilable
e. Marking : Not Available

As requested, the sample was subjected to **the Tests as per IEC 61111 Edition 2.0 2009-04** and the results noted below:

2. Visual Inspection (Cl. 5.2)

a. Classification : Class 0
b. Dimensions : 3.1mm X 1m X 5m
c. Workmanship and finish : Satisfactory
d. Sample Color : Dark Grey

Tested By

V. Sivaguru
SO Electrical

Checked & Approved By

Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH(SR)/EL(C)/2020/0049B-M	29.10.2020	Manual	02	05

3. Tests

Sl.No	Tests	Observed Values	Specified limits
1.	**Mechanical Puncture resistance** (as per cl. 5.5.2 of the specification) Number of specimens: 2 Size of specimen: 50mm (diameter) Test carried out on both the sides of the matting for two specimens. 5mm diameter needle produce a taper with an include angle of 12° and tip rounded to 0.8mm **Puncture resistance in N** i. Side 1 ii. Side 2 iii. Average	 116 118 117	 Min. 70
2.	**Voltage Proof test** (as per cl. 5.6.2.2.2 of the specification) Number of specimen: 1 A 1270mm x 1270mm sheet of 5mm thick Plexiglass material with picture frame of 762 mm x 762 mm opening the center placed on a grounded metal plate. Mask filled with a conductive material same as thickness to bring the ground electrode at the same level to maintain direct contact with the mat to be tested. (fig:1 of IEC 61111 Edition 2.0 2009-04) An ac voltage of 5kV (rms) at 50 Hz applied and kept constant for 3 minutes.	Withstood the test satisfactorily	Shall withstand test voltage without break down or flashover

Tested By
V. Sivaguru
SO Electrical

Checked & Approved By
Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH(SR)/EL(C)/2020/0049B-M	29.10.2020	Manual	03	05

Sl.No	Tests	Observed Values	Specified limits
3.	**Voltage Withstand Test** (as per cl. 5.6.2.3 of the specification) Number of specimen: 3 Specimen size : 150 x 150 Electrode : 25mm (Top) x 75mm (Bottom) 10kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec.	Withstood the test satisfactorily	Shall withstand test voltage without break down or flashover
4.	**Ageing test** (as per cl. 5.7 of specification) Number of specimen: 2 Sample conditioned at 70°C for 168 hours. **Mechanical Puncture resistance** (as per cl. 5.5.2) Test carried out on both the sides of the matting for two specimens. **Puncture resistance in N** i. Side 1 ii. Side 2	 96 98	 94(Min) (Minimum 80% of puncture resistance before ageing)
5.	**Flame retardance test** (as per cl.5.8.1 of the specification) Number of specimen: 1 Specimen size: 150 x 150mm Application of flame 10s and after withdrawal, the propagation of flame was observed for 55s and it shall not reach any point of 50mm diameter.	 Satisfactory No appreciable flame observed	 Propagation of flame shall not reached 50 mm diameter of circle

Tested By

V. Sivaguru
SO Electrical

Checked & Approved By

Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH(SR)/EL(C)/2020/0049B-M	29.10.2020	Manual	04	05

Sl.No	Tests	Observed Values	Specified limits
6.	**Acid resistance** (as per cl. 5.9 of the specification) Number of specimen: 4 Size of specimen: 150 x 150mm Sample immersed in Sulfuric acid solution at 23°C±2°C for 8h. Following acid condition, the sample rinsed with water and dried for 2h at 70°C. **Mechanical Puncture resistance** (as per cl. 5.5.2) Test carried out on both the sides of the matting for two specimens. **Puncture resistance in N** i. Side 1 ii. Side 2 **Voltage Withstand Test** 10kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec.	 90 92 Withstood the test satisfactorily	 Min. 88 (Minimum 75% of puncture before acid resistance) Shall withstand test voltage without breakdown or flashover
7.	***Oil resistance** (as per cl. 5.10 of the specification) Number of specimen: 4 Size of specimen: 150 x 150mm Sample conditioned in air at a temperature of 23°C±2°C at 50% RH for 3h. Then the sample is conditioned by immersing in oil at a temperature of 70°C for 24h. Following oil condition, the sample dried using lint free clean cloth. **Mechanical Puncture resistance** (as per cl. 5.5.2) Test carried out on both the sides of the matting for two specimens. **Puncture resistance in N** i. Side 1 ii. Side 2 **Voltage Withstand Test:** 10kV ac voltage at 50 Hz applied with a rate of rise of 1000V/sec.	 92 91 Withstood the test satisfactorily	 Min. 88 (Minimum 75% of puncture without oil conditioning) Shall withstand test voltage without breakdown or flashover

Tested By
V. Sivaguru
SO Electrical

Checked & Approved By
Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

451173

ANNEXURE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Page
NTH(SR)/EL(C)/2020/0049B-M	29.10.2020	Manual	05	05

Sl.No	Tests	Observed Values	Specified limits
8.	**Low Temperature folding test** (as per cl. 5.8.2 of the specification) **Number of specimen: 3** Size of specimen: 200 x 500mm Sample conditioned at (-)25±3°C for 4 hours. After this the test piece folded at the midpoint and placed between two polyethylene plates and subjected to a force of 100N for 30s. **Visual inspection**	Satisfactory	Shall not show crack or tear break observed
	Voltage Withstand Test (An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 10kV).	No crack or tear break observed Withstood the test satisfactorily	Shall with stand without breakdown or flashover

Note:

i. The average ambient conditions of the laboratory during the above tests were as follows

Room Temperature : 27 ± 2°C

Relative Humidity : 70 to 75%.

ii. *The Oil Resistance test was carried out by transformer oil as requested by the firm.

Tested By

V. Sivaguru
SO Electrical

Checked & Approved By

Sriilayaraj Soundarrajan
Scientist-C(Electrical)

Notes : 1. The results relate only to the items tested or calibrated
2. The test/calibration certificate shall not be reproduced except in full, without written approval of the authority